




2602.39A

Non-Woven Single-Coated Tape



- Backing:** 2.4 oz/sy white thermoplastic polyurethane fabric
- Adhesive:** Medical-grade acrylic (M102)
- Liner:** 80lb super-calendared kraft, silicone release treated on both sides

Applications

- Medical device component
- Patient monitoring
- Medical device assembly
- Sensor components

Features

- PUR non-woven carrier
- Medical-grade Acrylic Adhesive
- 80lb Release Liner

Benefits

- Breathable for maximum patient comfort
- Highly conformable
- Designed for long-term wear applications
- Highly resistant to perspiration-borne moisture
- Easy to die-cut and convert

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/o liner	11.7 mils	0.297 mm	PSTC 133
Adhesive Thickness	4.5 mils	0.114 mm	PSTC 133
Liner Thickness	4.2 mils	0.107 mm	PSTC 133
Adhesion to Steel	100 oz/in	10.94 N/cm	PSTC 101 Mod

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-irritating, and non-sensitizing.

In accordance with FDA cGMP requirements, Berry Plastics reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

