

# 330X HVAC EXTREME WEATHER

FOIL TAPE



- Backing:** Aluminum Foil
- Adhesive:** Acrylic
- Liner:** Unbleached Natural Kraft Paper
- Specifications:** UL 723 Classified
- Colors:** Aluminum
- Available Size:** 2.83 in x 50.3 yd (72 mm x 46 m)

## Applications

- Sealing insulation and repairing in cooler/refrigeration applications
- Insulation seaming and patching
- Sealing joints and seams in duct work for A/C, heating and ventilation systems
- Emergency household and auto repairs

## Features

## Benefits

High Performance Acrylic Adhesive	<ul style="list-style-type: none"> <li>• Excellent performance in extreme indoor or outdoor temperatures</li> <li>• High tack, aggressive bond to surfaces</li> <li>• Non-solvent for less odor</li> </ul>
Aluminum Foil Backing	<ul style="list-style-type: none"> <li>• Conformable to fit corners and joints</li> <li>• Mold and mildew resistant</li> <li>• UV and moisture resistant</li> </ul>
Wide Width	<ul style="list-style-type: none"> <li>• 2.83" width allows for greater surface coverage and less overlaps</li> </ul>
UL 723 Classified	<ul style="list-style-type: none"> <li>• Meets flammability requirements for use on on Class 1 duct</li> </ul>
Low VOC Content	<ul style="list-style-type: none"> <li>• Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED®</li> </ul>

## Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	3.5 mils	89 µm	ASTM D-1000
<b>Adhesion to Steel</b>	55 oz/in	6.02 N/cm	PSTC-101
<b>Tensile Strength</b>	14 lb/in	24.53 N/cm	ASTM D-1000
<b>Operating Temperature</b>	-35 to 260 °F	-37 to 126 °C	
<b>Smoke Developed</b>	0		
<b>Flame Spread</b>	0		
<b>VOC Content</b>	< 30 g/L		
Recommended Storage Conditions: 60 - 80 °F at 40-60% RH Standard Shelf Life (at 25 °C): 36 months from date of manufacture			

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.