


Medical Transfer Tape



Release Liner **Liner:** 80# White Densified Kraft

Adhesive **Adhesive:** Acrylic (M129)

Applications

- Room temperature bonding to films, foams, and fabrics
- Excellent adhesion to skin

Features

Benefits

- | | |
|---|--|
| <ul style="list-style-type: none"> • Acrylic Adhesive • 80# Densified Kraft Liner | <ul style="list-style-type: none"> • Excellent peel and shear properties • Bonds well to a variety of substrates • Hypoallergenic • Conformable and good dimensional stability |
|---|--|

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	2.0 mils	0.051 mm	PSTC 133
Liner Thickness	4.0 mils	0.102 mm	PSTC 133
Adhesion to Steel (24 Hr Dwell)	60 oz/in	6.56 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (24 Hr Dwell)	88 oz/in	9.63 N/cm	PSTC 101 Mod - 4mil Alu Foil
Shear Strength (at 72 °F)	>7 Days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	-30 to 220 °F	-34 to 104 °C	

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic and non-irritating.

In accordance with FDA cGMP requirements, Berry Global reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.