

WW-RS SERIES

LINERLESS RUBBER SPLICING TAPE - 600V

DESCRIPTION

Rated up to 600V

WW-RS is a general-purpose ethylene rubber-based tape with excellent electrical, chemical and physical properties. WW-RS is a self-bonding tape that permits much quicker taping speeds than a tape with a liner and yields a uniform, void-free build-up. The excellent stretch of WW-RS allows conformability to the most complex shapes and contour. WW-RS is compatible with all extruded cable insulations and is specially formulated to have excellent thermal conductivity that will allow the heat to

Meets ASTM D-4388 SPECIFICATION (TYPE I, II, III)

FEATURES

- Self-bonding
- Outstanding corona and ozone resistance
- · High thermal conductivity and flame retardant

insulations and is specially formula	ated to have excellent thermal conductivity is flame retardant and meets typical indu			esistance	
	BACKING	ADHESIVE	COLOR	STANDARD SIZES (WIDTH X LENGTH)	PART NUMBER
TECHNICAL PROPERTIES	EPR Rubber	Acrylic adhesive	Black	.75" x 15' (19mm x 4.6m) 1" x 15' (25mm x 4.6m) 1.5" x 15' (38mm x 4.6m) 2" x 15' (51mm x 4.6m)	WW-RS-75 WW-RS-10 WW-RS-15 WW-RS-20
	CHARACTERISTIC	TYPICAL VALUE		TEST METHOD	
	Thickness (mils)	30		ASTM D 4325	
	Breaking strength (psi)	333.6		ASTM D 412	
	Elongation at break (%)	890		ASTM D 412	
	Fusion (78.74 mils max.)	No flag		ASTM D 4325	
	Heat resistance	266°F, 130°C		ASTM D 4325	
	Operating temp.: Continuous	194°F, 90°C		ASTM D 4325	
	Operating temp.: Emergency overload	266°F, 130°C		ASTM D 4325	
	Water absorption (%)	0.06		ASTM D 570	
	Ozone resistance	Pass		ASTM D 4325	
	UV resistance	Pass		ASTM D 4325	
	Dielectric strength (V/mil)	990.6		ASTM D 149	
	Dissipation factor after water immersion	0.005		ASTM D 150	
	Dissipation factor after hot water immersion	0.015		ASTM D 150	
	Dielectric constant after water immersion	2.9		ASTM D 150	
	Dielectric constant after hot water immersion	3.1		ASTM D 150	
	Volume resistivity (Ω.cm) 96h @ 23°C and 50% RH	1x10 ¹⁶		ASTM D 257	
	Volume resistivity (Ω.cm) 96h @ 23°C and 96% RH	1x10 ¹³		ASTM D 257	
RECOMMENDED USES		STORAGE		SHELF LIFE	

RECOMMENDED USES	STORAGE	SHELF LIFE
For insulating of splices on solid dielectric cable through 600 volts in conjunction with a jacketing tape.	In original packaging, placed in a horizontal position, covered, between 5°C and 35°C.	60 months from date of manufacture.

Data in table represents average test results and are not to be used for specification purpose. Users should test the products' suitability for their intended use themselves.

LIMITED WARRANTY: NSI Industries LLC warrants that each of its products will be free from material and manufacture defects at the date of shipment (unless specified otherwise). NSI Industries LLC makes or gives no warranty to the distributor, its customers, or the product's end user regarding the product's merchantability and/or suitability for their/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proven to be defective, NSI Industries sole obligation and buyer's exclusive remedy shall be through the distributor, at NSI Industries' discretion, to replace, repair, or refund the product proved to be defective within the time period specified above. EXCEPT AS EXPRESSLY SET FORTH HEREIN, NSI INDUSTRIES MAKES OR GIVES NO OTHER WARRANTIES, EXPRESSED OR IMPLIED. Except where prohibited by law, NSI Industries LLC will not be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products.

