


Double-Coated PET Film Tape



Liner:	80# Polycoated Kraft
Liner Side Adhesive:	Rubber (I919)
Backing/Carrier:	0.5 mil PET Film
Air Side Adhesive:	Rubber (I918)

Applications

- Die-cut abrasives, fabrics, and non-wovens
- Protective bumpers and floor graphics
- Bonding to flexible materials for clean removal uses
- Ideal for polishing pads, sanding disks, shelf strip labels

Features

- Rubber Adhesive
- Polyester Film Carrier
- 80# Kraft Liner

Benefits

- Differential adhesive provides clean removal on the liner side with strong bonding on the air side
- High shear, moderate peel strength
- Support for aid in processing and application
- Conformable
- Easily die-cut

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Overall Thickness (w/liner)	8.0 mils	0.203 mm	PSTC 133
Adhesive Thickness (Air Side)	1.8 mils	0.046 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Adhesive Thickness (Liner Side)	1.2 mils	0.030 mm	PSTC 133
Liner Thickness	4.5 mils	0.114 mm	PSTC 133
Adhesion to Steel (Air Side)	210 oz/in	22.97 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Liner Side)	55 oz/in	6.02 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Air Side)	290 oz/in	31.73 N/cm	PSTC 101 Mod - 2 mil Alu Foil
Adhesion to Steel (Liner Side)	110 oz/in	12.03 N/cm	PSTC 101 Mod - 2 mil Alu Foil
Shear Strength	>7 Days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.