


## Double-Coated Tape



<b>Liner:</b>	74# Polycoated Kraft
<b>Liner Side Adhesive:</b>	Acrylic (I630)
<b>Backing/Carrier:</b>	0.5 mil PET Film
<b>Air Side Adhesive:</b>	Acrylic (I630)

### Applications

- Bonding and laminating to a wide variety of cloth, vinyl, cork, paper, rigid and flexible plastics
- Paper splicing
- Mounting displays, signs, posters, mirrors, name-plates, and decorative wall products
- Applications requiring excellent UV and extreme temperature resistance

### Features

- Acrylic Adhesive
- Polyester Film Carrier
- 74# Polycoated Kraft Liner

### Benefits

- High tack adhesive with moderate shear strength
- Resistant to oils, plasticizers, and UV
- Excellent extreme temperature performance
- Support for aid in processing and application
- Conformable
- Conformable and good dimensional stability

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Overall Thickness (w/liner)</b>	8.6 mils	0.218 mm	PSTC 133
<b>Air-Side Adhesive Thickness</b>	1.3 mils	0.033 mm	PSTC 133
<b>Carrier Thickness</b>	0.5 mils	0.013 mm	PSTC 133
<b>Liner Side Adhesive Thickness</b>	1.3 mils	0.033 mm	PSTC 133
<b>Liner Thickness</b>	5.5 mils	0.140 mm	PSTC 133
<b>Adhesion to Steel (Air Side - Initial)</b>	40 oz/in	4.38 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Liner Side - Initial)</b>	40 oz/in	4.38 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Air Side - 24Hr Dwell)</b>	60 oz/in	6.56 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Liner Side - 24Hr Dwell)</b>	60 oz/in	6.56 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Air Side - Initial)</b>	70 oz/in	7.66 N/cm	PSTC 101 Mod - 4 mil Alu Foil
<b>Adhesion to Steel (Liner Side - Initial)</b>	70 oz/in	7.66 N/cm	PSTC 101 Mod - 4 mil Alu Foil
<b>Shear Strength</b>	>7 Days		PSTC 107 Mod
<b>Laminating Temperature</b>	68 to 100 °F	20 to 38 °C	
<b>Service Temperature</b>	-30 to 220 °F	-34 to 104 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at VYBOND GROUP, INC. (Vybond Group, Inc. 2320 Bowling Green Road, Franklin, KY 42134) by qualified technical personnel. To VYBOND's knowledge, it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which VYBOND assumes any legal responsibility.