



<b>Backing:</b>	2.5 mil clear polyethylene film with matte finish
<b>Adhesive:</b>	Non-sensitizing medical-grade acrylic (M153)
<b>Liner:</b>	80lb kraft, silicone release treated on one side

### Applications

- Surgical Drape Heat Lamination
- Medical device attachment
- Surgical Drape Attachment
- Drape to patient attachment

### Features

### Benefits

- |   |   |
|---|---|
| <ul style="list-style-type: none"> <li>• PE Film Backing</li> <li>• Medical-grade Acrylic Adhesive</li> <li>• 80lb Release Liner</li> </ul> | <ul style="list-style-type: none"> <li>• Matte finish for minimal glare</li> <li>• Highly conformable</li> <li>• Excellent adhesion to skin and drape materials</li> <li>• Easy to die-cut and convert</li> </ul> |
|---|---|

### Typical Test Values

	Standard UOM		Metric UOM		Test Method
<b>Total Thickness w/liner</b>	8	mils	0.203	mm	PSTC 133
<b>Adhesive Thickness</b>	1.2	mils	0.030	mm	PSTC 133
<b>Carrier Thickness</b>	2.5	mils	0.064	mm	PSTC 133
<b>Liner Thickness</b>	4.1	mils	0.104	mm	PSTC 133
<b>Adhesion to Steel</b>	90	oz/in	9.85	N/cm	PSTC 101 Mod
<b>Heat Seal Temperature</b>	200°F				

### Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-irritating, and non-sensitizing.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

The information presented herein was prepared at BERRY GLOBAL, INC by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.