

WW-GC SERIES GLASS CLOTH TAPE

| DESCRIPTION | | | | FEATURES | |
|---|--|---------------|--|---|----------------------|
| WW-GC is a woven glass fabric tape with a thermosetting rubber-based pressure-sensitive adhesive. It has high tensile strength and provides excellent tear and abrasion resistance with a service temperature rating of 266 °F. | | | High temperature resistant Service temperature of 266 °F High mechanical strength Thermosetting adhesive Abrasion resistant. | | |
| MATERIALS | BACKING | ADHESIVE | COLOR | STANDARD SIZES (WIDTH X LENGTH) | PART NUMBERS |
| | Glass cloth | Rubber based | White | 0.5" x 66' (12.7mm x 20.1m) 0.75" x 66' (19mm x 20.1m) | WW-GC-50 WW-GC-75 |
| | CHARACTERISTIC | TYPICAL VALUE | | TEST METHOD | |
| | Thickness (mils) | 7 | | ASTM D 1000 | |
| | | | | | |
| | Tensile strength (lb/in) | 17 | | ASTM D 100 | |
| TECHNICAL PROPERTIES | Tensile strength (lb/in) Elongation at break (%) | | | | 00 |
| | | | 5 | ASTM D 100 | 00 |
| | Elongation at break (%) | | 71 5 97 | ASTM D 100 ASTM D 100 | |
| | Elongation at break (%) Adhesion to steel (lb/in) | 0.0 | 71 5 97 5 | ASTM D 100 ASTM D 100 ASTM D 100 | |

For insulating and protection high-temperature connections on solid dielectric cable through 600 volts and securing WW-ARC Arc and Fire Proofing Tape where adhesion at high temperatures is required. Ideal for binding and harnessing applications.

In original packaging, placed in a horizontal position, covered, between 5°C and 35°C.

36 months from date of manufacture.

Data in table represents average test results and are not to be used for specification purpose. Users should test the products' suitability for their intended use themselves.

LIMITED WARRANTY: NSI Industries LLC warrants that each of its products will be free from material and manufacture defects at the date of shipment (unless specified otherwise). NSI Industries LLC makes or gives no warranty to the distributor, its customers, or the product's end user regarding the product's merchantability and/or suitability for their/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proven to be defective, NSI Industries sole obligation and buyer's exclusive remedy shall be through the distributor, at NSI Industries' discretion, to replace, repair, or refund the product proved to be defective within the time period specified above. EXCEPT AS EXPRESSLY SET FORTH HEREIN, NSI INDUSTRIES MAKES OR GIVES NO OTHER WARRANTIES, EXPRESSED OR IMPLIED. Except where prohibited by law, NSI Industries LLC will not be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products.

