Technical Data Sheet



Distributed in

The United States of America: Peter Kwasny Inc. 62-64 Enter Lane, Islandia, NY 11749 Canada by Peter Kwasny Spraypaint Canada Inc. 2275 Lakeshore Blvd. West, Suite 530 Toronto, ON. M8V 3Y3

Toll free North America
Phone: 1-844-426-6330 / Fax: 1-866-226-6434
order@kwasny.us / service@kwasny.us
www.spraymax.com

SprayMax® 2K Clear Glamour 335 g NET WT. 11.8 oz Art. Nr. 3680061



Product

Description / Purpose

Properties

Material base

Gloss level

Solid content

2K clear coat with very high chemical, gasoline, and weathering resistance for high-quality and longterm sealing of repair paint jobs and new paint jobs on cars and motorcycles.

- · Maximum resistance to abrasion and scratching
- · Very smooth flow
- · Lasting high gloss
- · Very good polish ability
- · No colour deviation
- · Outstanding painting surface
- Suitable even at higher ambient temperatures
- · Ideally suited for large surfaces

Two-component acrylic resins Activator: aliphatic isocyanates

high gloss

88+ / -4 gloss units at 20° measuring angle on

completely dried basecoats

33.8 % by weight relating to the diluted paint



EPA Coating Category

CCP Clear Coatings Product

PWR Limit 1.50

CARB Aerosol Rule Coating Category (01/2017)

TCC Two Component Coating

PWR Limit 1.20

Substrate

Solvent and waterborne base coat systems, old paint coats dried according to manufacturer's instructions (cleaned and sanded).

Processing

Protection measures



Wear personal protection equipment.

(respiratory mask / gloves / goggles)

For more information, see safety data sheet.

Shake



Before activating, shake can thoroughly for 2 minutes again from when the mixing balls are heard.

Place red button



Remove the red button from the cap. Turn the can by 180° and fit the button onto the pin.

Press red button



Turn the can upside down and place on a firm surface. Press the red button with the palm of your hand until it clicks into place.

Shake



After activating, shake can again thoroughly for 2 minutes, again from when the mixing balls are heard.

Spray to test



After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance



6 - 8 inches / 15 - 20 cm



Spray passes



Dry film thickness 1.6 mil (40 μm) (approx. 1 - 2 spray coats)

Flash-off time



Flash time:

approx. 10 - 15 min between each spray coat

Processing conditions



Optimum application at 64° F - 77° F (18° C - 25° C) and a relative humidity from 40 - 60 %.

Coverage



approx. $5.4 - 8.1 \text{ sq ft } (0.5 - 0.75 \text{ m}^2) / \text{aerosol at}$ approx. $1.2 - 2.0 \text{ mil } (30 - 50 \text{ } \mu\text{m}) \text{ dry film thickness}$

Drying



dust dry: 20 min

dry to touch: 250 min

Ready for assembling: 8 - 24 h (over Night)

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.



IR drying possible, Respect technical manual Forced dry 60 min at 140° F
10 min flash-off time before forced dry
IR drying 15 min

Pot life



Approx. 48 h at 68° F (20° C) room temperature and a relative humidity of approx. 40 - 50 %. The processing time depends on the ambient temperature. Higher temperatures reduce the pot life, lower temperatures will prolong it.

Finish



After painting, turn the can upside down and spray the valve until empty.



Additional Information

Shelf Life



36 months (not activated)

The usage period refers to an unused can that is stored correctly at a temperature of 68° F / 20° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved. We reserve the right to update, amend or supplement the content of the information without prior notice.