



Toll Free: 87 PERMATEX
(877-376-2839)

6875 Parkland Boulevard, Solon
Ohio 44139

Technical Data Sheet

Permatex® Medium Strength Threadlocker BLUE Gel

AAM 02/19

PRODUCT DESCRIPTION

Permatex® Medium Strength Threadlocker BLUE Gel is a medium strength anaerobic threadlocking gel conveniently packaged in a new Gel Twist™ or Gel Squeeze™ applicator. The product, like its liquid counterpart, is a single component, anaerobic gel that cures when confined in the absence of air between close fitting metal surfaces, ideal for all 6mm to 25mm (1/4 inch to 1 inch) diameter threaded assemblies. Excellent chemical resistance and temperature resistance range of -65°F to +300°F (-54°C to +149°C). The assembly is easily removable with hand tools for servicing requirements. NSF Nonfood Components Program Listed (P1) (135871).

PRODUCT BENEFITS

Improved Reliability

- Eliminates vibration issues
- Seals against leakage
- Prevents rusting of threads
- Designed for use on vertical or hard-to-reach applications
- Cures without cracking or shrinking
- Adjusts or disassembles with hand tools

Easy Application

- No mess Gel Twist™ or Gel Squeeze™ applicator
- Gel-type product does not drip when applied
- Single component
- No curing outside of joint
- Thixotropic: resists dripping from threads during assembly
- No torque compensation required during assembly

TYPICAL APPLICATIONS

Prevents loosening and leakage of threaded fasteners. Particularly suitable for applications such as:

- Belt tensioner bolts
- Pulley bolts
- Cup and core plugs
- Fan hub bolts
- Visor mount bolts
- Starter mounting bolts
- Alternator Mounting Bolts
- Intake Manifold Bolts
- Valve Cover Bolts
- Vacuum Adjustment Screws
- Oil Pan Bolts
- Axle Cover Screws
- Drive Shaft Bolts
- Disc Brake Caliper Bolts
- Gearshift Knobs

DIRECTIONS FOR USE

For assembly

1. Clean all threads (bolt and hole) with a cleaning solvent such as Permatex® Brake and Parts Cleaner and allow to dry. Remove the translucent protective cap by pulling off at an angle.
2. For Gel Twist™ turn the dial on the bottom of the container until 1/8" to 1/4" (3mm to 6mm) of material protrudes from the top of the application tip. Note: First time use may require 4 to 5 full turns of the dial before material appears in the tip. For Gel Squeeze™, remove cap and squeeze 1/8 to 1/4" (3mm to 6mm) of material beyond tip.
3. Apply threadlocker to the engagement area of the male fitting (usually the leading 5 to 6 threads).
4. Assemble parts and tighten to recommended torque.
5. If unused gel contacts metal threads, do not retract threadlocker back into the tube. Wipe off with a clean towel.
6. Replace protective cap.

For Cleanup

1. Residual liquid films and/or fillets outside the joint are readily soluble in Permatex® Brake and Parts Cleaner.
2. Cured product can be removed with a combination of soaking in Permatex® Gasket Remover and mechanical abrasion such as a wire brush.

For Disassembly

1. Remove with standard hand tools.
2. In the rare instance where hand tools do not work, because of excessive engagement length, apply localized heat to nut or bolt to approximately 450°F (232°C). Disassemble while hot.

For Reassembly

1. Remove loose product from nut and bolt following cleanup procedure above.
2. Apply Surface Prep™ activator to all threads, regardless of metal type and allow to dry.
3. Apply threadlocker gel as above.
4. Assemble and tighten as usual.

PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Anaerobic Dimethacrylate Ester
Appearance	Opaque Blue Fluorescent Gel
Specific Gravity	1.15
Viscosity @ 25°C, cP	
Brookfield RVF, spindle	Gel
#3, @ 20 RPM	
Flash Point (TCC), °F (°C)	>200 (>93)

NOT FOR PRODUCT SPECIFICATIONS.

THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.

PLEASE CONTACT PERMATEX, INC., TECHNICAL SERVICE DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS FOR YOUR SPECIFIC APPLICATION.

PERMATEX, INC., 6875 PARKLAND BOULEVARD, SOLON, OH 44139 PHONE - (1-877)PERMATEX

TYPICAL CURING PERFORMANCE**Cure speed vs. substrate**

The rate of cure will depend on the material used. Permatex® Medium Strength Threadlocker BLUE Gel will react faster and stronger with **Active Metals**. However, **Inactive Metals** will require the use of a primer (Surface Prep) to obtain maximum strength and cure speed at room temperature.

Active Metals	Inactive Metals
Soft Steel Iron	Bright Platings
Copper	Anodized Surfaces
Brass	Titanium
Manganese	Zinc
Bronze	Pure Aluminum
Nickel	Stainless Steel
Aluminum Alloy	Cadmium

Cure speed vs. temperature

The rate of cure will depend on the ambient temperature. **Full cure** is attainable in 24 hours at room temperature, 22°C (72°F), or 1 hour at 93°C (200°F).

Cure speed vs. primer

To shorten cure time or if an inactive surface is present, applying a primer (Surface Prep) to the surface will improve cure speed. A 3/8-16 steel nut and bolt assembly will fixture in 5 minutes using a primer, while fixturing will occur in 20 minutes without a primer. Full cure in 24 hours for both procedures.

PERFORMANCE OF CURED MATERIAL

(After 24 hr at 72°F on 3/8-16 steel Grade 8 Nuts and Grade 5 bolts)

	Typical Value
Breakaway Torque, Nm, (in.lbs)	13 (115)
Prevail Torque, Nm (in.lbs)	6 (53)

Where Breakaway Torque is the force required to initiate the fastener movement and Prevail Torque is the force required to disassemble the fastener once Breakaway Torque has occurred.

TYPICAL ENVIRONMENTAL RESISTANCE**Temperature Resistance**

Product temperature range from -54°C to +150°C (-65°F to +300°F). The Breakaway and Prevailing Torque values decrease as temperature increases, however the assembly remains effective against vibration and leakage.

Chemical / Solvent Resistance

The product retains effective properties in contact with automotive fluids, such as motor oil, gasoline, brake fluids, transmission fluids, alcohol and antifreeze solutions.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). It is recommended to confirm compatibility of the product with such substrates.

ORDERING INFORMATION

Part Number	Container Size
09978	1 g Gel Squeeze™ Pouch
24005	5 g Gel Squeeze™ Applicator, carded
24010	10 g Gel Twist™ Applicator, carded
24835	35 g Gel Tube, carded

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8° and 28°C (46° and 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications.