


PRELIMINARY



# 4390M-12PT

## Differential Double-Coated Polyester Film Tape



- Release Liner:** 12PT Polycoated Kraft
- Liner Side Adhesive:** Rubber (I924)
- Backing/Carrier:** 0.5 mil PET Film
- Air Side Adhesive:** Acrylic (I639)

### Applications

- Bonding to a variety of ether, ester, and low perm urethane foams
- LSE bonding including mica-filled polypropylene

Features	Benefits
<ul style="list-style-type: none"> <li>• Acrylic Adhesive</li> </ul>	<ul style="list-style-type: none"> <li>• Excellent heat resistance</li> <li>• Low fogging (tested at 24 hrs, 200 °F)</li> <li>• Biostatic additive resists microbial growth</li> </ul>
<ul style="list-style-type: none"> <li>• Polyester Film Carrier</li> </ul>	<ul style="list-style-type: none"> <li>• Support for aid in processing and application</li> <li>• Conformable</li> </ul>
<ul style="list-style-type: none"> <li>• Rubber Adhesive</li> </ul>	<ul style="list-style-type: none"> <li>• Offers exceptionally high tack and high peel</li> <li>• Designed for bonding to various foams, as well as rough and porous surfaces</li> </ul>
<ul style="list-style-type: none"> <li>• 12PT Polycoated Kraft Liner</li> </ul>	<ul style="list-style-type: none"> <li>• Rigid liner facilitates processing and application</li> <li>• Suitable for die-cutting and kiss cutting</li> </ul>

### Typical Test Values

	Standard UOM		Metric UOM		Test Method
<b>Overall Thickness (w/liner)</b>	16.2	mils	0.411	mm	PSTC 133
<b>Air-Side Adhesive Thickness</b>	1.9	mils	0.048	mm	PSTC 133
<b>Carrier Thickness</b>	0.5	mils	0.013	mm	PSTC 133
<b>Liner Side Adhesive Thickness</b>	1.8	mils	0.046	mm	PSTC 133
<b>Liner Thickness</b>	12.0	mils	0.305	mm	PSTC 133
<b>Adhesion to Steel (Air Side)</b>	60	oz/in	6.56	N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Liner Side)</b>	130	oz/in	14.22	N/cm	PSTC 101 Mod - 1 mil PET
<b>Shear Strength (Room Temp)</b>	7	days			PSTC 107 Mod
<b>Laminating Temperature</b>	68 to 100	°F	20 to 38	°C	
<b>Service Temperature</b>	30 to 180	°F	-1 to 82	°C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038  
 1-800-343-7875 Fax 1-800-328-4822  
 www.berryglobal.com

4/28/2022