



OE SHINY GALV

#16-842

A shiny galvanized coating that protects and matches new galvanized metal. Resists oxidation and eliminates the need for an aluminum topcoat. Excellent for restoration of chain link fences and guardrails. The dried paint film contains a minimum of 65% zinc. It is considered a sacrificial coating, and

meets ASTM A780 performance specifications.

Suggested Uses:

All vehicle bodies Agricultural, mining and construction equipment Piping, storage tanks Bridges Ships and marine equipment

Packaging:

UPC Code Cans per case Shipping weight per case Container Label weight Shipping Classification Hazard Class 043281006934

6 7 lbs. 16 fluid ounce can 13 ounces (369 grams) limited quantity, UN 1950 2.1

Properties:

Coverage Up to 15 square feet Cleanup Paint or lacquer thinner **Extremely Flammable** Flammability Flash point -4F Specific Gravity 0.87 Solids Content 18% % Zinc in dried paint film 68% MIR value 1.05, cannot exceed 1.25 HAPs content 15% Storage Temperature 40-100F Application Temperature 50-90F Durability Very Good Abrasion Resistance Good Heat Resistance 250F Resin System Epoxy Shelf life Guaranteed for 2 years

Dry Time*:

To touch 5 minutes To topcoat 20 minutes

*At 72F, 50% humidity, 1.5 mil thickness

Curing/Recoat time is extended with multiple coats and excessively thick coats

Gloss*: Flat, <15*

*as measured on a 60 degree gloss meter

3-23-2022

TECHNICAL DATA SHEET