



Toll Free: 87 PERMATEX
(877-376-2839)

6875 Parkland Boulevard, Solon
Ohio 44139

Technical Data Sheet

Permatex® Black Plastic Welder®

AAM Revised 01/19

PRODUCT DESCRIPTION

Permatex® Black Plastic Welder® is a structural adhesive designed for general purpose bonding of a wide variety of materials. Black Plastic Welder® forms a tough, durable bond to most plastics, composites, ceramics, and wood in any combination. It is a fast, hard setting product with a 5 minute working time and 10 minute fixture time. **NOTE: Permatex® Black Plastic Welder® will not bond polyethylene and polypropylene plastics.**

PRODUCT BENEFITS

- Bond sets in 10 minutes
- Requires no primers
- Room temperature cure
- Gap filling to 0.125 inch
- Bonds diverse substrates
- Water resistant
- Good chemical resistance


TYPICAL APPLICATIONS

Bonds rigid materials including:

- ABS
- Fiberglass
- PVC
- Vinyl
- FRP
- Acrylic
- Glass
- Styrene
- Wood
- SMC

DIRECTIONS FOR USE

1. Protect work area from accidental spills.
2. Surface must be clean, dry and free of grease & oil.
3. Roughen surfaces with sandpaper or other abrasives.
4. Remove the plastic tab from the tip of both nozzles.
5. Depress plunger on syringe to dispense Part A and Part B. Thoroughly mix on a clean, disposable surface for at least one (1) minute or until uniform in color.



6. Apply to surfaces being repaired. Assemble parts immediately. Remove excess adhesive immediately.
7. Allow bond to set for 8 – 10 minutes before moving or handling. Product fully cures within 24 hours.

For Cleanup

1. For any cleanup, use isopropyl alcohol before the material is allowed to dry.
2. Clean hands with Permatex® Fast Orange® hand cleaner or soap and water.

PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Structural acrylic
Mix ratio	1 : 1
Appearance	
Part A	Black
Part B	Amber
Odor	Acrid
Specific Gravity	0.94 – 1.0
Flash Point, TCC	51°F
Viscosity	Heavy syrup

CURING PROPERTIES

Working Time	4 - 6 minutes
Fixture Time	8 - 10 minutes
Final color	Black
Temperature range	-60°F to +250°F
Hardness	70D
Elongation	7%

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as an adhesive for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
84145	5 min. Black Plastic Welder®, 0.84 fl. oz. dual syringe, carded

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 46° to 82°F (8° to 28°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications.