

SUBMITTAL RECORD _____
 JOB _____
 LOCATION _____
 SUBMITTED TO _____
 SUBMITTAL PREPARED BY _____
 APPROVED BY _____
 DATE _____



Specification Form NPAB40/NPAB187 Adhesive Canister

DESCRIPTION

Duct liner is typically attached to duct walls by two fastening methods; one with mechanical fasteners and the other with adhesive. Mechanical fasteners are utilized to prevent delamination of the liner while adhesives bond the liner to the metal ensuring that air flow can not intrude between the two materials. The choice of an adhesive is affected by several factors some of which are; the method of application, acceptable dry time, solvent type.

Duro Dyne NPAB40/NPAB187 is a web type, general purpose adhesive that bonds well to a wide variety of substrates, with one side or two side application. This black liner adhesive can also be used as an effective edge coating**. It has a quick tack, is flexible and water proof.

FEATURES

- Dual Purpose: Liner Adhesive & Edge Coating!**
- Low VOC Organic Compound
- No Methylene Chloride (Dichloromethane)
- High Strength
- Flexible Non Wrinkling
- Fast Tacking
- Appropriate for Edge Coating**
- Waterproof

TYPICAL PROPERTIES

Color: Black

VOC: <80 gms./ltr.

Flammability: Flammable per ASTM E-681-04

Effect of Freezing: None

Storage Life: 15 months

Application Temperature: 65° F - 95° F

Maximum Service Temperature: 150° F

Estimated Coverage NPAB40: 2,250-2,700 Sq Ft @2.5-3 gm/Sq Ft

Estimated Coverage NPAB187: 10,125 Sq Ft @2.5-3 gm/Sq Ft

Method of Application: Attach spray hose and spray gun then fully open valve on canister. Hold spray gun tip 6 to 10 inches from surface to be covered, always at a 90° angle to surface. Apply even coats. Do not allow it to concentrate or puddle in one area. For best performance, use this product at room temperature.

**Where allowed by code and inspection authorities.



NPAB40



NPAB187

RELATED SMACNA RECOMMENDATIONS*

7.4 Installation Standards For Rectangular Ducts Using Flexible Liner

S2.3 Each layer of duct liner shall be attached with 90 percent coverage of adhesive at the liner contact surface area.

S2.4 All transversely oriented edges of liner not receiving metal nosing shall be coated with adhesive. Liner shall be neatly butted without gaps at transverse joints and shall be coated with adhesive at such joints before butting.

S2.6 Ducts with interior widths of 8 in. (203 mm) or less do not require mechanical fasteners in addition to adhesive.

**From SMACNA HVAC Duct Construction Standards Metal and Flexible • Third Edition • 2005*

NPAB complies with the South Coast Air Quality Management (SCAQMD) Rule #1168 and VOC (Volatile Organic Compound) standards and thus can be used for **IEQ Credit 4.1: Low Emitting Materials: Adhesives & Sealants** when used for field installation on the building interior and applied on-site.

ITEM#	CODE	DESCRIPTION
5116	NPAB40	40# Portable Adhesive Canister - Black Solvent Base
5118	NPAB187	187# Adhesive Canister - Black Solvent Base

SUGGESTED SPECIFICATIONS

All metal duct shall be lined according to SMACNA HVAC Duct Construction Standards. Each layer of duct liner shall be attached with 90% coverage of adhesive at the liner contact surface area. Adhesive shall be a non-chlorinated solvent based adhesive. Adhesive shall be supplied in a Portable Adhesive Canister-Black, code NPAB40/NPAB187, as supplied by Duro Dyne Corporation.

For canister disposal instructions, please visit our website at: <http://www.durodyne.com/AdhInsAhes.php>

For the NPAB187 *only*: RETURNABLE CYLINDER - For free pick up call 866-735-9876. Product # is 17-0000-2161-2

Duro Dyne Corporate Headquarters, Bay Shore, NY
 631-249-9000 • Fax: 631-249-8346
 Duro Dyne Midwest • Duro Dyne West • Duro Dyne Canada
www.durodyne.com • E-mail: durodyne@durodyne.com

©2020 DURO DYNE CORP.
 Printed in the USA 9/22/2020
 BO005441

